



EM3573/20

Clear Pu multi-coat

Main features of the product:

<ul style="list-style-type: none"> • Good hiding power • Good thixotropy 	<ul style="list-style-type: none"> • Easy sanding
--------------------------------------------------------------------------------------------------	------------------------------------------------------------------

Field application: wooden doors, furniture, kitchens cabinets

Gloss Versions : 20- Gloss

Substrate preparation: sanding wooden items whit grit 180

Application:	Spray gun, airless and air-mix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3573/20	100
	catalyst	EMC99	50
	Thinner	EM725	30÷40

Chemical-Physical Properties at 20°C

Solid content (%)	44±3
Specific gravity (g/cm ³) at 20°C	1.19± 0,03
Viscosity DIN 4 (s) at 20°C	40±5
Pot- life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	150- 180 g/m ²
Number of hands recommended	Min 1- max 2
Mix. Viscosity ready to use cup DIN 4 at 20°C	15-19 sec

General indications about the cycle

	Drying in tunnel at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sandable	4 h	2÷3h

Alternative thinners:

EM726	During the summer time
-------	------------------------

Storage:

Keep the cans carefully sealed, in a well-ventilated place and with a temperature controlled between 10-30°C

EM3573/20

Deadline:

12 months from date of manufacture when stored according to directions above