



EM3884/XX

Transparent Polyurethane Top coat

Main features of the product:

Applied by spraying High hiding power High solid contain	Excellent smoothness Excellent matting uniformity
--	--

Application field: wooden doors, furniture, doors

Gloss level : 05-10-20-30-50-60-80-90 Gloss

Substrate preparation: substrate overcoating with PU or PE sealer sanded with 320 grit

Application:	Spray gun, airless and airmix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3884/XX	100
	Catalyst	EMC15-EMC17	50
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid Content (%)	50±3
Specific gravity (g/cm ³) at 20°C	0.99± 0,030
Viscosity DIN 4 (s) at 20°C	50±5
Pot life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	120 -150 g/m ²
Number of hands recommended	1
Mix. Viscosity ready to use cup DIN 4 at 20°C	14-15 sec

General indications about the cycle

	Drying at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Stackable	5÷6h	3-4 h

Alternative Hardeners:

EMC6S NY not-yellowing	50%
------------------------	-----

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C
--

EM3884/XX

Deadline:

12 months from date of manufacture when stored according to directions above