



EM811

White polyester sealer

Main features of the product:

<ul style="list-style-type: none"> • Easy sanding • Recommended for cycles of MDF supports • Good thixotropy 	<ul style="list-style-type: none"> • Good coverage • Good distension
---	--

Application fields : wooden doors, furniture, kitchen doors

Substrate preparation :Sanding the surface of wooden items and MDF using a grit 180

Application:	Spray gun, airless and air-mix with double mix equipment		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM811	100
	catalyst	EM10830	2
	accelerator	EM10811	2
	Thinner	EM739	20

Chemical-Physical Properties at 20°C

Solid content (%)	95±1
Specific gravity (g/cm ³) at 20°C	1.50± 0,03
Viscosity BROOKFIELD (mpa*s) at 20°C	7000±800
Pot- life (min) at 20°C	30÷40 min

Application Characteristics

Quantity recommended per coat	200-250 g/m ²
Number of hands recommended	Min 1- max 3
Time between coats	min: 20' max: 40'

General indications about the cycle

	Drying in tunnel at 20'(min)	Drying in tunnel at 40'(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sandable	6 h	3÷4 h

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C

Deadline:

6 months from date of manufacture when stored according to directions above

