



## EM837

### Transparent polyester sealer

**Main features of the product:**

<ul style="list-style-type: none"> <li>• Easy sanding</li> <li>• Good transparency</li> </ul>	<ul style="list-style-type: none"> <li>• Good coverage</li> <li>• Good distension</li> <li>• Suitable for flat plane</li> </ul>
---	---

**Application fields** : wooden doors, furniture, panels

**Substrate preparation:** Sanding the surface of wooden items using a grit 180 on exotic woods is suitable apply a specific isolator before polyester sealer

<b>Application:</b>	Spray gun, airless and airmix		
<b>Mixing preparation:</b>	Product	Code	% weight
	Part "A"	EM837	100
	catalyst	EM10830	2
	accelerator	EM10811	2
	Thinner	EM739	20

**Chemical-Physical Properties at 20°C**

Solid content (%)	94±3
Specific gravity (g/cm <sup>3</sup> ) at 20°C	1.050± 0,030
Viscosity BROOKFIELD (mpa*s) at 20°C	3000±500
Pot life (min) at 20°C	20÷30 min

**Application Characteristics**

Quantity recommended per coat	300 g/m <sup>2</sup>
Number of hands recommended	Min 1- max 3
Time between coats	min: 20' max: 40'

**General indications about the cycle**

	Drying in tunnel at 20'(min)	Drying in tunnel at 40'(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sandable	6 h	3÷4 h

**Storage:**

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C