



EM3715

Transparent PU sealer

Main features of the product:

Can be applied by spray Shorter sanding time Medium coverage: suitable for both open pore to pore closed	Suitable for a wide range of supports, Resistant to removal
--	--

Field application: wooden doors, furniture, kitchen cabinets

Substrate preparation: sanding wooden items whit grain 180

Application:	Spray gun, airless and airmix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3715	100
	catalyst	EMC99	50
	Thinner	EM725	20-30

Chemical-Physical Properties at 20°C

Solid content (%)	42±3
Specific gravity (g/cm ³) at 20°C	0.973± 0,030
Viscosity DIN 4 (s) at 20°C	35±5
Pot life (h) at 20°C	3-4 h

Application Characteristics

Quantity recommended per coat	120- 150 g/m ²
Number of hands recommended	Min 1- max 2
Mix. Viscosity ready to use cup DIN 4 at 20°C	14-19 sec

General indications about the cycle

	Drying at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Sandable	4 h	2-3 h

Alternative thinners:

EM726 During the summer months or when ambient temperatures and humidity are high

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C