

EM3741



EM3741

Transparent PU tixot sealer

Main features of the product:

High hiding power Easy sanding Good transparency	Excellent thixotropi Good elasticity Suitable for electrostatic application
--	---

Application field : wooden doors, furniture, doors

Substrate preparation: sanding wooden items or MDF

Application:	Spray gun, airless and airmix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3741	100
	catalyst	EMC15	50
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid Content (%)	45±1
Specific gravity (g/cm ³) at 20°C	0.98± 0,030
Viscosity FORD 6 (s) at 20°C	60±5
Pot life (h) at 20°C	3-4 h

Application Characteristics

Quantity recommended per coat	150-180 g/m ²
Number of hands recommended	Min 1- max 4
Mix. Viscosity ready to use cup DIN 4 at 20°C	17-19 sec

General indications about the cycle

	Drying in tunnel at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sandable	4÷5 h	2÷3h

Alternative thinners:

EM726	During the summer time
-------	------------------------

Storage:

Keep the cans carefully sealed, in a well-ventilated place and with temperature controlled between 10-30 °C

Deadline:

12 months from date of manufacture when stored according to directions above