

EM3776



EM3776

Transparent PU sealer

Main features of the product:

Easy sanding Good open pore	High transparency Good distension
--------------------------------	--------------------------------------

Application field : wooden doors, furniture, panels

Substrate preparation: sanding wooden items with grit 180

Application:	Spray gun, airless and air-mix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3776	100
	catalyst	EMC99	50
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid content (%)	42±3
Specific gravity (g/cm ³) at 20°C	1.00± 0,030
Viscosity DIN 4(s) at 20°C	40±5
Pot life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	80- 100 g/m ²
Number of hands recommended	Min 1- max 2
Mix. Viscosity ready to use cup DIN 4 at 20°C	14-17 sec

General indications about the cycle

	Drying in tunnel at 20(min)	Drying in tunnel at 40(min)
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Sandable	4÷5 h	3÷4 h

Alternative thinners:

EM726 During the summer time

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C

Deadline:

12 months from date of manufacture when stored according to directions above