



## EM7007/XX

### White Polyurethane converter top- coat

**Main features of the product:**

Applied by spraying Good resistance to "metal marking" Suitable for tinting system	High coverage Good softness to the touch White converter for tinting system
--	---

**Application field :** wooden doors, furniture, kitchens cabinets

**Gloss Versions :** 05-10-20-30-50-60-80 Gloss

**Substrate preparation:** substrate over-coated with PU or PE sealer sanded with 320 grit

<b>Application:</b>	Spray gun, airless and air-mix		
<b>Mixing preparation:</b>	Product	Code	% weight
	Part "A"	EM7007/XX	100
	Catalyst	EMC6S NY	50
	Thinner	EM725	20-30

**Chemical-Physical Properties at 20°C**

Solid Content (%)	51±1
Specific gravity (g/cm <sup>3</sup> ) at 20°C	1.26± 0,03
Viscosity DIN 4 (s) at 20°C	80±5
Pot- life (h) at 20°C	3÷4 h

**Application Characteristics**

Quantity recommended per coat	120 -150 g/m <sup>2</sup>
Number of hands recommended	Min: 1 Max:2
Mix. Viscosity ready to use cup DIN 4 at 20°C	14-15 sec

**General indications about the cycle**

	<b>Drying at 20°C</b>	<b>Drying in tunnel at 40°C</b>
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Stackable	5÷6h	3÷4h

**Alternative thinners:**

EM726	During the summer time
-------	------------------------

**Storage:**

Keep the cans carefully sealed, in a well-ventilated place and with temperature controlled between 10-30 °C
---

**Deadline:**

12 months from date of manufacture when stored according to directions above
--