



EMCONV7000

Clear converter top-coat

Main features of the product:

<ul style="list-style-type: none"> • Applicable by spray • NOT suitable as a clear top-coat 	<ul style="list-style-type: none"> • Suitable as a transparent converter for tinting system • Good softness to the touch • Fast curing
---	---

Application field : wooden doors, furniture, kitchens cabinets, panels

Gloss level : 05-10-20-30-50-60-80 Gloss

Substrate preparation: substrate overcoated with PU or PE sealer sanded with grit 320

Application:	Spray gun, airless and air-mix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EMCONV7000	100
	Catalyst	EMC6S	50
	Thinner	EM724	20-30

Chemical-Physical Properties at 20°C

Solid Content (%)	58±1
Specific gravity (g/cm ³) at 20°C	1.06± 0,03
Viscosity DIN 4 (s) at 20°C	90±5
Pot life (h) at 20°C	3 ÷4 h

Application Characteristics

Quantity recommended per coat	120 -150 g/m ²
Number of hands recommended	1
Mix. Viscosity ready to use cup DIN 4 at 20°C	14÷15 sec

General indications about the cycle

	Drying at 20°C	Drying in tunnel at 40°C
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Stackable	5÷6h	3÷4h

Alternative thinners:

EM726	During the summer time
-------	------------------------

Storage:

Keep the cans carefully sealed, in a well-ventilated place and with temperature controlled between 10-30 °C

Deadline:

12 months from date of manufacture when stored according to directions above
--