



EM7940

Black PU sealer

Main features of the product:

<ul style="list-style-type: none"> • General use • Good sandability • high hiding power 	<ul style="list-style-type: none"> • Good elasticity • Fast curing
--	--

Field application: wooden doors, furniture

Substrate preparation: sanding wooden items or MDF whit grain 180, on very porous supports (MDF) is suitable apply an insulator

Application:	Spray gun, airless and airmix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM7940	100
	catalyst	EMC99	50
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid contents (%)	65±3
Specific gravity (g/cm ³) at 20°C	1.27± 0,030
Viscosity DIN 4 (s) at 20°C	60±5
Pot life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	150- 180 g/m ²
Number of hands recommended	Min 1- max 4
Mix. Viscosity ready to use cup DIN 4 at 20°C	17-19 sec

General indications about the cycle

	Drying at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sanding	4÷5 h	1÷2h

Alternative thinners:

EM726	During the summer time
-------	------------------------

Storage:

Keep the cans carefully sealed, in a well-ventilated place and with temperature controlled between 10-30 °C

EM7940

Deadline:

12 months from date of manufacture when stored according to directions above
--