

EM7993



EM7993

White PU tixo sealer

Main features of the product:

High hiding power Easy sanding	Excellent thixotropi Good elasticity For application on MDF is recommended one hand of insulator
-----------------------------------	--

Application field : wooden doors, furniture, kitchens cabinets

Substrate preparation: sanding wooden items or MDF with grain 180

Application:	Spray gun, airless and air-mix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM7993	100
	catalyst	EMC51S or EMC99	50
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid Content (%)	69±3
Specific gravity (g/cm ³) at 20°C	1.46± 0,030
Viscosity FORD 6 (s) at 20°C	75±5
Pot- life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	150-180 g/m ²
Number of hands recommended	Min 1- max 4
Mix. Viscosity ready to use cup DIN 4 at 20°C	17-19 sec

General indications about the cycle

	Drying at 20(min)	Drying in tunnel at 40(min)
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Sanding	4÷5 h	2÷3h

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C

Deadline:

12 months from date of manufacture when stored according to directions above