



## EM858

### White Polyurethane Insulator

**Main features of the product:**

<ul style="list-style-type: none"> <li>• Applicable by spray</li> <li>• Good isolation</li> </ul>	<ul style="list-style-type: none"> <li>• Suitable for MDF edges, before the sealer application</li> </ul>
---	---

**Field application:** wooden doors, furniture

**Substrate preparation:** sanding wooden items or MDF whit grain 180

<b>Application:</b>	Spray gun, airless and air-mix		
<b>Mixing preparation:</b>	Product	Code	% weight
	Part "A"	EM858	100
	catalyst	EMC15	50

**Chemical-Physical Properties at 20°C**

Solid contents (%)	62±3
Specific gravity (g/cm <sup>3</sup> ) at 20°C	0.98± 0,030
Viscosity FORD 6 (s) at 20°C	34±5
Pot life (h) at 20°C	3÷4 h

**Application Characteristics**

Quantity recommended per coat	60-80 g/m <sup>2</sup>
Number of hands recommended	Min 1- max 3
Mix. Viscosity ready to use cup DIN 4 at 20°C	8-10 sec

**General indications about the cycle**

	Drying at 20°C(min)	Drying in tunnel at 40°C(min)
Dry dust free	20	15
Imprint free	35÷40	20÷25
Sandable	4÷ h	2÷3h

**Storage:**

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C

**Deadline:**

12 months from date of manufacture when stored according to directions above