



EM369

White Nitro Sealer

Main features of the product:

| | |
|---|--|
| <ul style="list-style-type: none"> • Easy sanding • Fast drying | <ul style="list-style-type: none"> • High coverage • Good removal resistance |
|---|--|

Application field : wooden flat parts, furniture, doors

Substrate preparation: sanding wooden items whit grain 180

| | | | |
|----------------------------|--------------------------------|-------|----------|
| Application: | Spray gun, airless and air-mix | | |
| Mixing preparation: | Product | Code | % weight |
| | Part "A" | EM369 | 100 |
| | Thinner | EM713 | 30÷50 |

Chemical-Physical Properties at 20°C

| | |
|---|-------------|
| Solid contents (%) | 49±3 |
| Specific gravity (g/cm ³) at 20°C | 1.23± 0,030 |
| Viscosity FORD 6 (s) at 20°C | 55±5 |

Application Characteristics

| | |
|---|---------------------------|
| Quantity recommended per coat | 100- 140 g/m ² |
| Number of hands recommended | Min 1÷2 |
| Mix. Viscosity ready to use cup DIN 4 at 20°C | 17-19 sec |

General indications about the cycle

| | Drying at 20°C(min) | Drying in tunnel at 40°C(min) |
|---------------|---------------------|-------------------------------|
| Dry dust free | 20 | 15 |
| Imprint free | 35÷40 | 20÷25 |
| Sandable | 60÷90 | 30÷40 |
| Stackable | 3÷4 h | 2÷3 h |

Storage:

Keep the cans carefully sealed, in a well-ventilated place and with temperature controlled between 10-30 °C

Deadline:

12 months from date of manufacture when stored according to directions above