



EM3782

Transparent PU sealer for parquet

Main features of the product:

<ul style="list-style-type: none"> • Fast curing speed • Good covering 	<ul style="list-style-type: none"> • High transparency • Excellent mechanical resistance
--	--

Application field : wooden parquet

Substrate preparation: sanding wooden items whit grit 180

Application:	Spray gun, airless and air-mix		
Mixing preparation:	Product	Code	% weight
	Part "A"	EM3782	100
	catalyst	EMC02	100
	Thinner	EM731	20-30

Chemical-Physical Properties at 20°C

Solid content (%)	50±3
Specific gravity (g/cm ³) at 20°C	1.00± 0,030
Viscosity DIN 4 (s) at 20°C	55±5
Pot÷ life (h) at 20°C	3÷4 h

Application Characteristics

Quantity recommended per coat	120- 150 g/m ²
Number of hands recommended	Min 1- max 2
Mix. Viscosity ready to use cup DIN 4 at 20°C	14-19 sec

General indications about the cycle

	Drying at 20°C	Drying in tunnel at 40°C
Dry dust free	20 min	15 min
Imprint free	35÷40 min	20÷25 min
Sanding	4÷5 h	2÷3 h

Alternative thinners:

EM726	During the summer time
-------	------------------------

Storage:

Keep the cans carefully sealed, in a well-ventilated and temperature controlled between 10-30 °C
--

Deadline:

12 months from date of manufacture when stored according to directions above
--